

2P14/PA



Classic Mechanical

9kt

GENERAL INFORMATION

Carats: 9kt, suitable also for 14kt (see specific tech data sheet)
 Colour: deep yellow
 Advised use: mechanical works

| | | | | | | | | |
|------------------|----------|---|--------|---|------|---|--------|---|
| MECHANICAL WORKS | stamping | ■ | chains | ■ | tube | ■ | spring | ■ |
|------------------|----------|---|--------|---|------|---|--------|---|

Density: 11,05 g/cm³
 Hardness (as cast): 102 HV
 Hardness (after cold work 70%): 215 HV
 Hardness (after annealing): 100 HV

DIRECTIONS FOR SUGGESTED USE

Melting temperature: 910 °C

Casting temperature:
 80 °C over its melting temperature for continuous casting with sinker thermocouple.
 100 °C over its melting temperature to cast into ingot-mould and continuous casting.

Ingot-mould temperature: 150 °C

Cooling of ingots: quick in lukewarm water (about 40 °C)

Annealing: 650 °C for 20 minutes followed by a quick cooling in hot water (40 °C min.)

HINTS

- ❖ Recommended Pandora Alloys 9kt yellow solders: TG9 (soft), MG9 (medium), FG9 (hard)
- ❖ Recommended Pandora Alloys 9kt yellow alloy for casting: 2P14EC/CASTING

The above directions are only indicative. Strong variations to the above data are possible, depending on personal experience. Please, do not hesitate to contact us for further information.

Tech Chart and Safety Data Sheet available on our website www.pandoralloys.com