

Via Galvani, 14 - 20094 Corsico (MI) - Italy Tel. (+39) 02 45864035 - Fax (+39) 02 45869840 e-mail: info@pandoralloys.com Internet: www.pandoralloys.com

## 2P2022/U

DATA	
SHEET	

TECH



## GENERAL INFORMATION

Carats: Colour: Advised use: 22 kt, suitable also for 21 kt (see specific tech data sheet) rich yellow universal

CASTING	closed systems	open systems	pre-s	set st	ones	
MECHANICAL WORKS	stamping	chains	tube		spring	

Density: Hardness (as cast): Hardness (after cold work 70%): 17,43 g/cm<sup>3</sup> 95 HV 188 HV

## DIRECTIONS FOR SUGGESTED USE

Melting temperature:

Casting temperature:

100 °C over its melting temperature to cast into ingot-mould and continuous casting.

950 °C

100 °C over its melting temperature to cast with centrifugal machines.

120 °C over its melting temperature to cast in vacuum machines with controlled atmosphere.

140 °C over its melting temperature to cast in outdoor cylinders with vacuum.

Cylinders temperature:	from 550 °C to 650 °C depending on the machine and objects dimensions.					
Ingot-mould temperature:	150 °C					
Cooling casted objects:	in water after 10 minutes.					
Cooling of ingots:	quick in lukewarm water (about 40 °C)					
Annealing:	680 °C for 20 minutes followed by a quick cooling in hot water (40 °C min.)					

## HINTS

Recommended Pandora yellow 21 kt solder: TG21

The above directions are only indicative. Strong variations to the above data are possible, depending on personal experience. Please, do not hesitate to contact us for further information.