DATA SHEET 18 kt 4N pink (EN28654 Compliant) colour coordinates: L*=83.5 a*=8.8 b*=26.2 pre-set stones systems

Hardness (as cast): Hardness (after age hardening):	187 HV 284 HV
DIRECTIONS FOR SUGGESTED USE	
Melting temperature:	890°C
Casting temperature: 100°C over its melting temperature to cast with centrifugal machines 120°C over its melting temperature to cast in vacuum machines with controlled atmosphere 140°C over its melting temperature to cast in outdoor cylinders with vacuum	
Cylinders temperature:	from 550°C to 650°C depending on the machine and objects dimensions.
Cooling casted objects:	in water after 10 minutes
Annealing:	650°C for 20 minutes followed by a quick cooling in how water (40°C min.)
Age hardening:	Step 1: solubilization 680°C for 30 minutes. Cooling quickly in warm water (about 40°C).
	<i>Step 2: hardening</i> 300°C for 2 hours. Cooling at room temperature
HINTS ✤ Recommended Pandora 4N pink 18 kt solders: T4NJ (soft), M4NJ (medium), F4NJ (hard)	
The above directions are only indicative. Strong variations to the above data are possible, depending on personal experies Please, do not hesitate to contact us for further information.	
PINK YELLOW ALLOYS	Rev.5



GENERAL INFORMATION

CASTING

Via Galvani, 14 - 20094 Corsico (MI) - Italy Tel. (+39) 02 45864035 - Fax (+39) 02 45869840

e-mail: info@pandoralloys.com Internet: www.pandoralloys.com

Colour:

Density:

Advised use:



casting

closed

systems

15,02 g/cm³

andora

alloys

High Performance Casting

open

TECH