

Via Galvani, 14 - 20094 Corsico (MI) - Italy Tel. (+39) 02 45864035 - Fax (+39) 02 45869840 e-mail: info@pandoralloys.com Internet: www.pandoralloys.com



OTT85CAST



High Performance Casting

COSTUME JEWELRY

GENERAL INFORMATION

Carats: NONE - to be used without gold

Color: deep yellow color coordinates: L*=87.3 a*=4.6 b*=19.7

Advised use: casting

CASTING	closed systems		open systems		pre-set stones	
---------	----------------	--	--------------	--	----------------	--

Density: 8,65 g/cm³ Hardness (as cast): 100 HV

DIRECTIONS FOR SUGGESTED USE

Melting temperature: 920° C

Casting temperature:

100° C over its melting temperature to cast with centrifugal machines.

140° C over its melting temperature to cast in outdoor cylinders with vacuum.

120° C over its melting temperature to cast in vacuum machines with controlled atmosphere.

Cylinders temperature: from 550° C to 650° C depending on the machine and

objects dimensions.

Cooling casted objects: in water after 10 minutes.

Annealing: 650°C for 20 minutes followed by a guick cooling in hot

water (40°C min.)

The above directions are only indicative. Strong variations to the above data are possible, depending on personal experience. Please, do not hesitate to contact us for further information.