

Via Galvani, 14 - 20094 Corsico (MI) - Italy Tel. (+39) 02 45864035 - Fax (+39) 02 45869840 e-mail: info@pandoralloys.com Internet: www.pandoralloys.com



OTT.67/33M2

COSTUME JEWELRY

GENERAL INFORMATION

Carats: NONE - to be used without gold

Color: yellow color coordinates: L*=88.9 a*=1.5 b*=23.6

Advised use: casting

CASTING closed systems open systems pre-set stones

Density: 8,43 g/cm³ Hardness (as cast): 101 HV

DIRECTIONS FOR SUGGESTED USE

Melting range (Solidus – Liquidus): 890 - 900 °C

Casting temperature:

100 °C over its Liquidus temperature to cast with centrifugal machines.

120 °C over its Liquidus temperature to cast in vacuum machines with controlled atmosphere.

140 °C over its Liquidus temperature to cast in outdoor cylinders with vacuum.

Cylinders temperature: from 550 °C to 650 °C depending on the machine and

objects dimensions.

Cooling casted objects: in water after 10 minutes.

Annealing: 670 °C for 20 minutes followed by a quick cooling in hot

water (40 °C min.)

The above directions are only indicative. Strong variations to the above data are possible, depending on personal experience. Please, do not hesitate to contact us for further information.