

TBJPD

SOLDERING
ALLOY
SOFT 18kt

GENERAL INFORMATION

Carats: 18 kt
Colour: white
Specific usage: soldering alloy for white gold

White solder alloy without Nickel

DIRECTIONS FOR SUGGESTED USE

Melting temperature in 18kt: 1100°C
Ingot-mould temperature: 150°C
Cooling of ingots: quick in lukewarm water (about 40° C)
Annealing: 750°C for 20 minutes followed by a quick cooling in hot water (40° C min.)
Flowing temperature: 925° C

IMPORTANT NOTICE:

Use vertical ingot molds closed on all sides. Open ingot molds should not be used, to avoid cracking during rolling.

HINTS

- ❖ Recommended Pandora Alloys ready-to-use solders 18kt soft, medium and hard available in plates and sticks for yellow gold, red gold and white gold

The above directions are only indicative. Strong variations to the above data are possible, depending on personal experience. Please, do not hesitate to contact us for further information.